



ROOFARMOR

DTM

Polyurea-Urethane High Performance Coating

Typical Properties PSE 4170A-UV-M2-FR-SIL A (Isocyanate)

Viscosity, mPas @ 25° C	500-600
Specific Gravity @ 25° C	1.25
Wt./gallon @ 25° C lbs/gal	10.4
Appearance @ 25°C:	viscous liquid

Typical Properties PSE 4170A-UV-M2-FR-SIL B (Resin Polyol)

Viscosity, mPas @ 25° C	550-750
Specific Gravity @ 25°C:	0.984
Wt./gallon @ 25° C lbs/gal	8.2
Appearance @ 25°C:	viscous liquid

Product Description:

PSE 4170A is a 100% solids aromatic polyurethane-urea hybrid coating designed to be an elastomeric coating for all substrates, providing excellent chemical and abrasion resistance.

Unique Properties:

PSE 4170A combines the processing advantages of a polyurea with the economical performance of a polyurethane coating.

- Improved low temperature flexibility
- Improved tensile and elongation properties
- Lower sensitivity to moisture during application
- Improved low temperature cure
- Aluminum UV resistance

Application:

PSE 4170A can be built up to any thickness. A minimum of 30 mils in two passes is recommended for exterior applications.

Basic Uses:

- Water proofing for DTM (Direct To Metal) and Urethane (SPF) Foam Roofing
- Secondary containment coating to provide a chemical resistant membrane over prepared concrete and steel
- Gasoline and chemical resistance for Styrofoam flotation
- Abrasion resistance over wood, metal and concrete.
- Water and chemical resistance for ICF block, concrete Block and poured concrete walls.

Storage and Handling:

Containers for both A and B components should be kept tightly closed to prevent moisture contamination. Do not reseal if contamination is suspected. Use of a dry nitrogen blanket for partial drums is recommended. Component B may be stored at ambient temperatures. Component A should be stored between 77°F (25°C) and 95°F (35°C). For best results, this product should not be allowed to freeze, although it may be re-heated in a well ventilated oven for a period of time to re-liquefy solid particles. To avoid product degradation, product temperature during re-heating should not exceed 140°F (60°C). An additional note of caution is that exposure to temperatures over 400°F (204°C) can create excessive pressure potentially causing containers to rupture.

WARRANTY: The information herein is believed to be accurate and reliable as of the date of issuance, but is subject to change without prior notice. It is up to the User to contact Polycoat Products to verify the correctness prior to ordering or specifying this product. Polycoat Products warrants this product for merchantable quality only, does not warranty against unknown risks that may or may not be present, nor do we assume any responsibility for coverage, performance, or injuries resulting from the use of this product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY POLYCOAT PRODUCTS EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OR LAW, OR OTHERWISE, INCLUDING MARKETABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Failure to strictly adhere to recommended procedures shall relieve Polycoat Products of all liability with respect to the product or the use thereof. The buyer assumes all risks whatsoever as to the use of these products and the Buyer's exclusive remedy as to any breach of warranty or negligence claim shall be limited to the purchase price of the materials and agrees that any and all litigation proceedings shall be according to the laws of California and shall be filed in the County of Santa Fe Springs, CA. Each person, firm, or corporation engaged in the application installation, disposal or any other use of the any of these products shall carefully determine whether there is a potential hazard associated with such product in a specific usage, and utilize all appropriate precautionary and safety measures as outlined in Local, State and Federal regulations governing the use or disposal of these products or the construction and/or renovation of structures.

Typical Physical Properties

Hardness	Shore A	66-72
Elongation, 25° C	%	420-480
Tensile Strength 25° C	PSI	1500-1600
Tear, Die C	PLI	200-230
Taber Abrasion, CS-17 wheel, 1000gr. Load		11.4 mg lost/1000 cycles
Water Absorption, 75 ° F 30 days	%	2
Moisture Vapor Transmission (30 mils)	(ASTM-E-96) Procedure B	<0.030 US Perms
Practical coverage @ 50 mils		3 gallons/100 SF

Processing Characteristics

Solids by weight and volume	%	100
Mix ratio by volume		1:1
Gel time @ 74°F	Sec.	5-7
A component temperature	°F	120-140
component temperature	°F	140-160
Line Temperature	°F	110-130

Do not breathe aerosol or vapors and avoid contact with skin and eyes. Exposure to vapors of heated MDI can be dangerous. To heat product properly, use well ventilated convection ovens or other methods that distribute heat evenly. Avoid using drum heaters or other heat sources that may cause excessive local heating.

Health and Safety Information:

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling any of the products listed above. Before working with these products, it is your responsibility to read and become familiar with the available information on its hazards, proper use and handling. This is extremely important and cannot be overemphasized. Information is available in several forms, e.g. material safety data sheets and product labels. To obtain this information, contact your Polycoat Products representative.